

# Technical Data Sheet

## Supa Cure

Water based curing compound

<b>Description</b>	: <b>Supa Cure</b> is a water based curing compound.
<b>Applications</b>	: Apply by means of a spray, sponge, cloth or mop.
<b>Customer Benefits</b>	<ul style="list-style-type: none"> <li>• Coverage: 0.200-0.285 litres per sq.m</li> <li>• Dries in 4 hours (to touch)</li> <li>• After 12 hours, not tacky or tracky if walked on.</li> <li>• Able to be sprayed on at 4°C.</li> <li>• Water loss: 0.055g per sq.m in 72hours.</li> <li>• Volatile portion: non-toxic or flammable</li> <li>• Dries to a clear film.</li> <li>• Does not discolour the end product.</li> </ul>
<b>Storage</b>	<p>: Product is to be stored in a cool, dry, stable temperature (non-heat fluctuating) environment, out of direct sun and UV Light to prevent quality loss.</p> <p>: Product should be kept away from direct natural elements and oxidizing agents.</p> <p>: All drummed concentrate should be stored indoors and protected from heat, humidity, light and dust.</p>

Typical Characteristics	Typical Properties	
	Units	Typical Result
Minimum film forming temperature	°C	3
Solid Content	%	11
Viscosity @ 25°C	cPs	+/- 500
pH	-	5.5

<b>Product Specifications</b>	: AASHO M148 Type 2					
<b>Packing</b>	<b>500ml</b>	<b>1Lt</b>	<b>5Lt</b>	<b>20Lt</b>	<b>210Lt</b>	<b>1 000Lt</b>
	<b>N</b>	<b>N</b>	<b>Y</b>	<b>Y</b>	<b>Y</b>	<b>Y</b>

Information in this TDS is from available published sources and internal analysis and is believed to be accurate. No warrant, express or implied, is made and Stacor (Pty) LTD assumes no responsibility resulting from the in-correct use of this TDS. The user must determine suitability of this information for his/her application.